

SFI TEST REPORT FOR LIGHT ALLOY WHEEL

Reference No.	100903		
Type	F14	Nominal designation of rim	22×10.5J
Offset (mm)	+49	P.C.D. (mm)	130
Number of bolt holes	5	Structure	1-PC
Material	A356-T6	Manufacturing method	FLOW FORMING

MODEL#CB42U

Corporate name: Forgestar

Contact: Wong



1. Tire used for test

Item	Nominal designation of tire
Radial load endurance test	315/50R22
Impact test	265/35R22

PCD ϕ 15.75*24.5 HUB:74.1

MAX LOADING:2200LBS

2. Testing conditions and results

(1) Rotary bending fatigue test

Date of test, (Month 08 (Day) 26 (Year) 2010)

Testing equipment approval number A-238

Bending moment during test (kgf.m)	Rotational speed for test	Damage to disk wheel	Loosening of tightening section	Evaluation
576	100,000 circles	None	OK	Qualified/Disqualified

Used in calculation of bending moment [kN]{kgf} r 997.92 (m) d 0.049(m) W 0.4445 (kgs)

Calculated bending moment value M [kNm] {kgfm} r 575.04(m) d (m)

(2) Radial load endurance test

Date of test, (Month) 08 (Day) 28 (Year) 2010

Testing equipment approval number B-224

Pre-test air pressure [kpa]{kgf/cm ² }	Radial load during test [kN]{kgf}	Rotational speed for test	Damage to disk wheel	Loosening of fixture section etc.	Evaluation
460	2246	500,000circles	None	OK	Qualified/Disqualified

Used in calculation of Radial load[kN]{kgf} Calculated Radial load Q 997.92 {kgf} W 2245.31 (kgs)

(3) Impact test 13°

Date of test, (Month) 08 (Day) 25 (Year) 2010

Testing equipment approval number C-297

Pre-test air pressure [kpa]{kgf/cm ² }	Total width (mm)	Weight mass (kg)	Drop height (mm)	Impact position (°)	Damage to disk wheel	Air leakage	Evaluation
200	269	779	230	0°/180°	NONE	OK	Qualified/Disqualified

(4) Overall evaluation: Qualified/Disqualified